



**P-D Refractories CZ a.s.**

**Technical Data**

**RUDOKIT**

Brand

**NT 1350**

Al <sub>2</sub> O <sub>3</sub>	%	38
Fe <sub>2</sub> O <sub>3</sub>	%	0,6
TiO <sub>2</sub>	%	0,3
Na <sub>2</sub> O+K <sub>2</sub> O	%	3,5
Zrnitost (max.zrno)	mm	0-0,5
Žárovzdornost	ISO	166
Max.teplota použití	°C	1350
Vlhkost	%	18
Ztráta Žíháním	%	-3,4

The technical data represent average reference values established by DIN and EN test producers in our ceramic laboratory. They serve to give general information, they are liable to natural deviations, depending on production and shapes, and they are not to be cited as guaranteed properties or guaranteed values

4/30/2013